

Technical Data Sheet

PANAX Yellow GF-967T

Revision: March 2024

PRODUCT DESCRIPTION

Color Index	Pigment Yellow 13
C.I. No.	21100
Chemical Type	Disazo
CAS No.	5102-83-0
EU No.	225-822-9

PHYSICAL PROPERTIES


pH (2% aqueous)	6 ~ 8	ISO 787-9
Specific gravity	1.4g/cm ³	ISO 787-10
Bulk Density	590cm ³ /100g	ISO 787-11
Oil absorption	30g/100g	ISO 787-5

FASTNESS PROPERTIES

Acid	5	DIN EN ISO 20105-A03
Alkali	5	DIN EN ISO 20105-A03
Water	5	ISO 2836
Ethanol	4	ISO 2836
Xylene	4	ISO 2836
MEK	4	ISO 2836
DOP	5	ISO 2836
Heat/150°C, 10min.	4	ISO 787-21
Heat/200°C, 10min.	3	ISO 787-21
Light 1/3 SD	5	ISO 105-B01
Light 1/25 SD	3	ISO 105-B01

FULL SHADE

TINT SHADE



APPLICATION

Oil Ink	
Solvent Base Ink	
Water Base Ink	●
Paint (Oil Base)	
Thermoplastic Hot-Melt	
Plastics	
Textile Printing	
Artist Colors	

● = Recommended ○ = Potentially recommended

CHARACTERISTICS

Transparency	
Color Shade	
Others	

STANDARD PACKING

Paper bags	10kg
Big bags type C	On request

Product end-use application information is based on our current knowledge. It is presented without any representation or warranty concerning the suitability, performance, or correctness of the product for a particular application or end-use.

Significant variations can occur between lab test results and results obtained in actual end-use. We strongly advise customers to test the product in the specific intended applications under conditions expected during use.

HEAD OFFICE

UKSEUNG CHEMICAL CO., LTD.
 #174, GAEJWA-RO, GEUMJEONG-GU, BUSAN, KOREA / 46259
 Tel: +82-51-718-5345 ~ 5348
 Fax: +82-51-529-7272
 E-mail: trade@ukseung.co.kr
<http://www.ukseung.co.kr>

EUROPE OFFICE

UKSEUNG EUROPE GMBH
 Carl Benz Str. 5 D-68723 Schwetzingen, Germany
 Tel: +49 6094 9897 426
 Fax: +49 6026 9897 427
 E-mail: rainer.schubert@ukseung-europe.com
<http://www.ukseung-europe.de>