













# FLUORESCENT PIGMENT

												
GRADE	LEMON YELLOW	YELLOW	ORANGE YELLOW	ORANGE	ORANGE RED	RED	PINK	ROSE	VIOLET	MAGENTA	BLUE	GREEN
FB	203	205	207	305	400	403	503	507	605	707	805	905
UFB	203	205	207	305	400	403	503	507	605	707	805	905
FL	203	205		305	400	403	503	507	605	707	805	905
FLL-D		205D		305D		403D	503D		605D	707D	805D	905D
FP		117 3000									1050	1025
PA		205	207	305	400	403	503	507	605	707	805	905
PT		205		305		403	503		605		805	905
NFC		205		305		403	503		605	707	805	905
FD		1205		1305		1403	1503		1605	1707	1805	1905

## GENERAL INFORMATION



GRADE	PROPERTIES	AV.PARTICLE SIZE	OIL ABSORPTION	HEAT RESISTANCE	CHEMICAL RESISTANCE	MAIN APPLICATION
FB	High Intensity Colors Water & Solvent Based Systems	3 ~ 5 $\mu$ m	49	150°C	GOOD	Paints/Inks, Screen Inks, Paper Coatings, Rubbers, Plastics, Dispersions
UFB	Excellent Dispersibility Good Chemical Resistance	3 ~ 5 $\mu$ m	49	150°C	GOOD	Paints/Inks, Screen Inks, Paper Coatings, Rubbers, Plastics, Dispersions
FL	Good Heat Stability Low Formaldehyde Bleed Resistant Easily Dispersed	3 ~ 5 $\mu$ m	45	230°C	EXCELLENT	Plastics, EVA, PVC, Plastisol, Paints/Inks, Aerosols, Rubbers, Textiles
FLL-D	Ultra Low Formaldehyde Good Heat Stability Excellent Lightfastness	3 ~ 5 $\mu$ m	45	230°C	EXCELLENT	Plastics, EVA, PVC, Plastisol, Paints/Inks, Aerosols, Rubbers, Textiles
FP	Very Low Formaldehyde Good Heat Stability	2 ~ 5 $\mu$ m	60	230°C	GOOD	Plastics, EVA, PVC, Specialty Ink, Paints
PA	Formaldehyde Free Excellent Heat Stability Low Plate-out	40 ~ 60 $\mu$ m	-	280°C	MODERATE	Polyolefin Plastics (PE, PP), PVC, ABS, PC, PET, PS, PA, PU
PT	Formaldehyde Free Excellent Heat Stability Good Lightfastness	5 ~ 8 $\mu$ m	-	280°C	MODERATE	Water Based Ink & Paint Plastics, PVC Sol, EVA,

GRADE	PROPERTIES	AV.PARTICLE SIZE	pH	SOLID CONTNET	LIGHT FASTNESS	MAIN APPLICATION
NFC	Pigment Dispersion Formaldehyde Free Superior Workability	0.2 $\mu$ m	6.5 ~ 7.0	42 ~ 46%	4 ~ 5	Roll Printing, Screen Printing Padding Process, Garment Dyeing
FD	Pigment Dispersion Formaldehyde Free High Color Strength	0.2 $\mu$ m	6.5 ~ 7.0	42 ~ 46%	4 ~ 5	Roll Printing, Screen Printing Padding Process, Garment Dyeing

### UKSEUNG CHEMICAL CO., LTD.

Head Office : #174, Gaejwa-Ro, Geumjeong-Gu, Busan, Korea / 45259, TEL. : +82-51-523-1515 ~ 8, [www.ukseung.co.kr](http://www.ukseung.co.kr) / [trade@ukseung.co.kr](mailto:trade@ukseung.co.kr)  
 Seoul Office : #536, Central Blue, Avenue Fran, 25 Seouldaehak-Ro, 264 beon-Gil, Siheung-Si, Gyeonggi-Do, Korea / TEL : +82-31-433-1326  
[skw125@ukseung.co.kr](mailto:skw125@ukseung.co.kr)